

TECHNICAL DATA SHEET

JOKISCH KORIA NEFO 24.24 (Jokisch Corrosion Protection Wax 70)

Long term corrosion protection wax, that guarantees very long lasting protection, even under adverse condition like sea-transport.

APPLICATION

Can be applied by dipping, brushing or spraying. The residue film offers reliable protection against corrosion and can easily be removed with hydrocarbon cleaner or aqueous alkaline cleaner.

CHARACTERISTICS

- Universally applicable corrosion protection product
- Very high viscous
- Builds a brown, waxy protective film
- Water displacing
- Ready to use and easy to remove (cleaning: with commercially available cleaner)
- Easy to manage
- Free of barium compounds to ensure increased occupational safety for the user

CORROSION PROTECTION TIME

Indoor storage: 24 months

Outdoor storage: 24 months

TECHNICAL SPECIFICATIONS


	UNIT	METHOD	JOKISCH KORIA NEFO 24.24
Kin. viscosity at 20°C	mm ² /s	ASTM D 7042	80
Density at 20°C	g/cm ³	DIN 51 757	0,85
Flash point	°C	ASTM D93	39
Salt spray test		-	48h= R 0-1

This information is based on the latest state of knowledge. They are intended to describe the product and thus do not have the meaning to assure certain properties. A liability can not be derived from this.

STORAGE

Storage temperature: 5 – 40°C

Storage time: 36 months



JosS d.o.o.

General Distributor for Slovenia, Croatia, BiH, Serbia,
Montenegro, Kosovo and North Macedonia

Sokolska 45 | 2000 Maribor | Slovenia
T +386 2 421 57 20 | GSM +386 41 705 509
joss@joss.si | www.joss.si

