

# F.L. 20/50/88 N/125/250/ 1000/2000

Chain lubricants



## The benefits at a glance

- NSF-H1 registered
- Fully synthetic
- Minimum friction and wear
- Ageing and oxidation resistant
- Good creep and adhesive properties
- Favourable in processing



### Properties

**Rivolta F.L. 20 / 50 / 88 N / 125 / 250 / 1000 / 2000** are fully synthetic high performance chain lubricants for the food industry. A combination of high quality synthetic base oils free from mineral oil in combination with an efficient additive package gives a performance spectrum to our products which is far superior to conventional oils. So, the anyhow outstanding features of the base oils in view of wear protection, ageing stability and corrosion protection are increased by adding highly effective additives.

### Fields of application

- Chains:
  - For the inside bearing lubrication of highly loaded chains and for the complete lubrication in dusty surroundings (**Rivolta F.L.50 / 88 N / 125**), for the outside lubrication of chains in humid atmosphere or at high speeds (**F.L. 1000**) etc.
  - For the lubrication of conveyor chains, transport chains, timing chains, driving chains at conveyors (e.g. bottle/bottle case conveyors and routing installations; slaughter house conveyors), bakery conveyors etc.
- Levers, bolts, joints, guidings, slideways, rope lubrication, spindles and deflection rollers
- Cleaning and lubrication:
  - F.L. 88 N** penetrates coatings, dewateres, releases rust and pollution and cleans parts, penetrates tight tolerances very well and guarantees a portative inside bearing lubricating film.

### Material compatibility

Our **Rivolta F.L.** chain lubricants do not attack metals, plastics, lacquers and sealing materials which are resistant to mineral oil. The products are miscible and compatible with mineral oil.


### Preparation of the lubricating point

Please remove contaminations and residues as far as possible. The friction points should be dry if possible to achieve the full adhesive strength of the products.

### Instructions for use

Suitable application devices and accessories in our [accessories brochure](#).

<b>Form</b>	liquid
<b>Colour</b>	transparent
<b>Odour</b>	neutral



	Value							Norm
	F.L. 20	F.L. 50	F.L. 88 N	F.L. 125	F.L. 250	F.L. 1000	F.L. 2000	
<b>NSF Reg.-No.</b>	139533	023935 / 131279 (Ae)	141608 / 150461 (Ae)	023931	023933 / 127663 (Ae)	023930 / 130082 (Ae)	139831 / 139832 (Ae)	-
<b>Density at +15 °C</b>	0,83 g/cm <sup>3</sup>		0,85 g/cm <sup>3</sup>		0,86 g/cm <sup>3</sup>		0,87 g/cm <sup>3</sup>	DIN 51757
<b>Viscosity index</b>	> 120	> 140			> 150			DIN ISO 2909
<b>Kine. Viscosity at +20 °C</b>	38 mm <sup>2</sup> /s	80 mm <sup>2</sup> /s	240 mm <sup>2</sup> /s	290 mm <sup>2</sup> /s	990 mm <sup>2</sup> /s	4400 mm <sup>2</sup> /s	16000 mm <sup>2</sup> /s	DIN 51562-1
<b>Kine. Viscosity at +40 °C</b>	15 mm <sup>2</sup> /s	32mm <sup>2</sup> /s	85 mm <sup>2</sup> /s	100 mm <sup>2</sup> /s	220 mm <sup>2</sup> /s	1500 mm <sup>2</sup> /s	5000 mm <sup>2</sup> /s	DIN 51562-1
<b>Kine. Viscosity at +100 °C</b>	4 mm <sup>2</sup> /s	5,3 mm <sup>2</sup> /s	13 mm <sup>2</sup> /s	14 mm <sup>2</sup> /s	25 mm <sup>2</sup> /s	135 mm <sup>2</sup> /s	350 mm <sup>2</sup> /s	DIN 51562-1
<b>Flash point</b>	> +200 °C							DIN EN ISO 2592
<b>Pourpoint</b>	-65 °C	-62 °C	-55 °C	-50 °C	-40 °C	-15 °C	-12 °C	DIN ISO 3016
<b>Temperature range</b>	-62 °C up to +100 °C	-60 °C up to +140 °C	-35 °C up to +140 °C	-45 °C up to +140 °C	-40 °C up to +140 °C	-12 °C up to +140 °C	-10 °C up to +140 °C	-



**JosS d.o.o.**

Sokolska 45 | 2000 Maribor | Slovenia  
 T +386 2 421 57 20 | GSM +386 41 705 509  
 joss@joss.si | www.joss.si